

Construction
and repair

Agriculture

Textile
products

Maritime
applications

Industry

Basalt Reinforcing Geogrid 3x3 mm

Item-No. 030.0003.10.10

Basalt Fiber Geo-grid Certificate of Analysis					
					QJ 8.6.4-08-06
Delivery time: 2019-7-8			Specification:		
Batch No. : 201906F29			Basalt Fiber Mesh without coating 3*3-160g/m ²		
Quantity: 112m ²			Quality Standard: Q/GBF 031-2016		
Inspection records					
No.	Project		Standard Requirements	Test results	Results
1	weave	-	Mesh without coating	Line	Qualified
2	Exterior	-	No dirty or oil spot, or defects which affect to use	Line	Qualified
3	width	cm	112±1%	112	Qualified
4	warp net center-to-center spacing	mm	3±1	3.2	Qualified
5	weft net center-to-center spacing	mm	3±1	3.6	Qualified
6	Gram Weight	g/m ²	160±8%	162	Qualified
7	Combustible-matter content	%	1.0±0.3	1.06	Qualified
8	Warp Break Strength	N/50mm	≥750	779	Qualified
9	Weft Break Strength	N/50mm	≥750	1011	Qualified
Integrated to determine:					
Upon examination of this batch of qualified products					
Re-Checker: JC1			Checker: JC3		Date: 2019-7-8